

ANNEX

In Annex XVII to Regulation (EC) No 1907/2006, the following entry is added:

| | |
|-------------------------------|---|
| “65. Inorganic ammonium salts | <ol style="list-style-type: none"><li data-bbox="561 539 1088 1249">1. Shall not be placed on the market, or used, in cellulose insulation mixtures or cellulose insulation articles after <i>(date - two years after the entry into force of this Regulation)</i> unless the emission of ammonia from those mixtures or articles results in a concentration of less than 3 ppm by volume (2,12 mg/m³) under the test conditions specified in paragraph 4. A supplier of a cellulose insulation mixture <u>containing inorganic ammonium salts</u> shall inform the recipient or end user of the maximum permissible loading rate of the cellulose insulation mixture, expressed in thickness and density. A <u>downstream n-end</u>-user of a cellulose insulation mixture <u>containing inorganic ammonium salts</u> shall ensure that the maximum permissible loading rate communicated by the supplier is not exceeded.<li data-bbox="561 1263 1088 1480">2. By way of derogation, paragraph 1 shall not apply to placing on the market of cellulose insulation mixtures intended to be used solely for the production of cellulose insulation articles, or to the use of those mixtures in the production of cellulose insulation articles.<li data-bbox="561 1516 1088 1733">3. In the case of a Member State that, on <i>(date - the date of entry into force of this Regulation)</i>, —has national provisional measures in place that have been authorised by the Commission pursuant to Article 129(2)(a), the provisions of —paragraphs 1 and 2 shall apply from that date.<li data-bbox="561 1767 1088 1874">4. Compliance with the emission limit specified in the first sub-paragraph of paragraph 1 shall be demonstrated in accordance with Technical Specification |
|-------------------------------|---|

← **Formatiert:** Zeilenabstand: einfach

| | |
|--|---|
| | <p>CEN/TS 16516, adapted as follows:</p> <ul style="list-style-type: none">(a) the duration of the test shall be at least 14 days instead of 28 days;(b) the ammonia gas emission shall be measured at least once per day throughout the test;(c) the emission limit shall not be reached or exceeded in any measurement taken during the test;(d) the relative humidity shall be 90% instead of 50%;(e) an appropriate method to measure the ammonia gas emission shall be used;(f) the loading rate, expressed in thickness and density, shall be recorded during the sampling of the cellulose insulation mixtures or articles to be tested.” |
|--|---|